



# TuningFilm 800 BF – Stellar

## Technical Data Sheet

#### PRODUCT DESCRIPTION

TF 800 BF Stellar is 120µm cast vinyl coated with a low tack micro-structured acrylic adhesive.

## **CONSTRUCTION**

#### Face material:

120 µm sparkling double layer cast vinyl, cadmium-free.

#### Adhesive:

Repositionable clear solvent based acrylic adhesive.

#### Liner:

Highly stable 145 gsm white micro-embossed PE coated paper.

#### **TYPICAL USES**

TF 800 BF Stellar is designed for Vehicle & Boat Hulls Wrapping (above water line).

It can also be used for various furniture's & interior decorations.

## EXPECTED DURABILITY

Expected durability of the unprocessed product is up to:

Interior decoration: 10 years

Exterior application:

Vertical exposure	Zone 1	Zone 2	Zone 3
All Colours	5 years	4 years	3 years

Horizontal exposure	Zone 1	Zone 2	Zone 3
All Colours	3 years	2 years	Not Recom

This information is based on successful real life experience and artificial aging according to ISO 4892-2.

Boat application: above data reduced by 30%

**Zone 1:** North, West, Central & Eastern Europe, North America (excl. : USA desert's - zone 3)

**Zone 2:** South Europe, Central & South America, Asia Pacific, Australian South coastal area (from Perth to Brisbane), New Zealand

**Zone 3:** Greater Middle East, Africa, Australian Desert areas & North of Perth-Brisbane coastal area, USA (Arizona, California, Florida, Nevada, New Mexico, Texas, Utah), Mexico

## **SHELF LIFE**

2 years stored at 15-25°C and  $\pm$  50 % relative humidity.

## **PHYSICAL PROPERTIES** (Typical values)

**Thickness** (mm) (Film + adhesive) ISO 543

Face Material Data. 23°C DIN ISO 527-3

Tensile strength :> 35 N/15mmElongation at break :> 150 %

#### Adhesive Data, 23°C

FTM 1

Peel adhesion 180° on stainless steel (N/25mm)

- 20 min. residence: 17- 24 hour residence: 19- 1 week residence: 21

## **Dimensional stability**

FTM 14

Shrinkage (48 hours at  $70^{\circ}$ C): < 0.25mm

## **Temperature ranges:**

Application :  $+15^{\circ}$ C to  $+40^{\circ}$ C End-use :  $-40^{\circ}$ C to  $+90^{\circ}$ C

**Flammability** ISO 3795 Sample mounted on aluminium: self-extinguishing.

#### Solvent and chemical resistance

Resistant to most oils and grease, fuel, aliphatic solvents, weak acids, salts and alkalis.

#### **PROCESSING**

## Clean and degrease the substrate

All surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination. Use soapy water to remove the dust and degrease with isopropylic alcohol.

## **Application**

#### on flat or slightly curved surfaces

Apply TF 800 BF Stellar with dry application method.

#### on convex areas

Heat the film with a heat gun before conforming it over the convex area.

## on corrugated or concave areas

If the film is stretched into a corrugation it may pop-out after a few weeks.

It is, therefore, recommended <u>to cut</u> the film and to apply it in the corrugation without tension.

#### on rivets

Apply the film over the rivet with high pressure and heat it with a heat gun (air temperature over  $500^{\circ}$ C).

The film may lift slightly after few weeks.

# Application on boat

We recommend edge sealing.

#### Removability

Once heated, TF 800 BF Stellar is very easy to remove, leaving almost no adhesive residue on car body.

Some adhesive residue may be expected on gel coat after film removal.

Eventual adhesive residues can be removed with isopropylic alcohol.

Removability is warranted only on original manufacturer coating.

## Important remark

Compatibility with paints and lacquers should be tested by the end-user, prior to use.

issue 5 HGP 06/2016 Page 1 / 2





## **IMPORTANT NOTICE**

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.