

TK 911W P



PRODUCT INFORMATION

Product Description

Face Material:	75 µ White gloss, polymeric stabilized, soft calendered PVC film
Adhesive:	Permanent grey acrylic adhesive
Liner:	White PE coated Kraft liner 140 gsm

Typical Uses

Long term outdoor advertising or promotion on flat or curved surfaces.
Grey coloured adhesive of increased opacity.

Printing

Especially designed for solvent based & UV inkjet printing on wide-format printing equipment. The PEcoat liner is particularly indicated for printers using 'eco-solvent' or 'mild solvent' inks giving superb print results for high quality & high resolution printing.
On demand: ICC profiles. Please contact us.

Physical properties of the unprinted film

	Average values	Test method
Adhesive Data, 23°C		
Quick Tack on glass	12 ± 3 N/25 mm	FTM 9
Peel 24 hours on glass	18 ± 3 N/25 mm	FTM 1
Dimensional stability		
shrinkage: 48 hours at 70°C (applied on aluminium)	max 0.5 mm	FTM 14
Flammability	Self-extinguishing when applied on Alu panels	
Temperature ranges		
Minimum application temperature:	+ 10°C	
Service temperature range:	- 20°C to + 70°C	



thyssenkrupp

Shelf Life

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

Durability

The outdoor durability of the unprinted film is 7 years.

Overlamination of the inkjet printed material delays eventual colour fading that may occur upon time. This colour fading is dependent from the quality of the inkjet inks and the self-adhesive materials being used. We recommend the use of laminating film TK 111C or TK 121C series.

Chemical Resistance

TK 911W P is resistant to most oils and fats, fuels, aliphatic solvents, mild acids, salts and alkali such as:

Test agent	Test period	Test result
Salt water at 10°C to 75°C	2000h	No effect
Motor Oil 20W/50W	500h	No effect
Transmission Fluid	500h	No effect
Anti-Frost liquid	500h	No effect
Petrol	24h	No effect

Test method : Samples of TK 911W P were applied to enamelled steel-sheet one hour before testing. Samples were immersed in the specified test-agent at room temperature then removed after the indicated testing period.

Recommendations

Always test the combination of TK 911W P print media, inks and laminating film prior to commercial use.

Laminating conditions: Please ensure the print is perfectly dry. The printed material should be left to dry for at least 48 hours prior to lamination or transport.

Don't take shortcuts when drying graphics !

Drying of the graphics can be accelerated by passing a cold air flow over the print by means of an air blower mounted at the bottom of a drying fan.