

## Description

DETAFLX 1500 is a high-quality, fast moisture curing, permanently elastic, low modulus, one component polyurethane sealant which forms a permanent weather-proof bond to many surfaces. DETAFLX 1500 has a high resistance to weather conditions and high and low temperatures -50°C to +80°C.

## Application

DETAFLX 1500 is designed for bonding and sealing different substrates in construction industry and navigation and parquet gluing. DETAFLX 1500 has an excellent adhesion to most materials such as wood, concrete, metals, anodised aluminium, natural and artificial stone. Use a primer on porous surfaces and on plastics. DETAFLX 1500 can be repainted. Preliminary tests may be recommended.

## Joint Measures

Joint Width	Joint Depth	Allowed Difference
3-4mm	4-5mm	±1mm
6mm	6mm	±1mm
8mm	6mm	±1mm
10mm	6-8mm	±2mm
15mm	10mm	±2mm
20mm	10-12mm	±2mm
25mm	15mm	±2mm

## Processing Temperature

From +8°C up to +35°C

## Surfaces

All surfaces need to be dry, clean and free from dust or grease. When necessary, degrease with Parasilico Cleaner, MEK, alcohol or ethanol. If necessary, use primer. It is recommended that adhesion tests are carried out to determine the

suitability of the product for its application. When in doubt, contact our technical support service.

## Primers

	Colour	Drying Time
DL 2001	Transparent	±20 minutes

## Tooling

When needed with DL 100 or tools.

## Cleaning

Before Vulcanisation - Parasilico Cleaner  
After Vulcanisation - Remove as much as possible mechanically; the remainders of the P.U. sealant with Silicone Remover.

## Repairing

With the same product

## Available Colours

Cartridges of 310 ml: black, white, brown & grey.  
Sausages of 600 ml: black, white, brown & grey.  
Other colours: upon request.

## Limitations

Do not use as glazing sealant or mirror adhesive. Good ventilation is important during application and vulcanisation of the product.

## Shelf Life

12 months in unopened packing and kept in dry and cool conditions between +5°C and +25°C.

## Packing

25 cartridges of 310 ml/box  
20 sausages of 600 ml/box

## Method of Use

With a gun (manual or pneumatic). If no more than 90% of joints are vulcanised, 5% movement

This technical data sheet replaces all previous editions. The data on this sheet has been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.

is admitted.


## Precautions

Harmful. Contains isocyanate. Follow instructions of producer. See safety data sheet.

## Technical Approvals



Label SNJF Facade nr 4042, mastic type élastomère 25<sup>E</sup>.



## Technical Characteristics

### Non Vulcanised Sealant

Basis	Polyurethane
Vulcanisation System	1-C P.U.
Skinning Time (23°C and 50% R.H.)	90-150 min.
Vulcanisation Speed (23°C and 50% R.H.)	3mm/day
Density (ISO 1183)	1,17 g/ml

### Vulcanised Sealant

Shore A Hardness (ISO868)	25
Maximum Joint Distortion	25%
Modulus at 100% elong. (ISO 8340)	< 0,40 N/mm <sup>2</sup>
Ultimate Elongation at break (ISO 8339) %	> 400 %
Temperature Resistance	-50°C / +80°C

## Polyurethane Sealants Chemical Compatibilities

To determine the good compatibility of a PU sealant, 6 dumbbells are moulded following the ISO 8339 (1984). After curing 28 days at 23°C and 50% R.H. three dumbbells are pulled, the three remaining dumbbells are immersed in the checked product. The compatibility is considered as good if after one month immersion the tensile at break variation is not upper than 50% compared to untreated dumbbells and if the adhesion is good.

This technical data sheet replaces all previous editions. The data on this sheet has been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.

	Products	Compatibility	Note
<b>Acids</b>	10% Acetic Acid	Good	
	25% Acetic Acid	Poor	Sealant Swelling
	10% Hydrochloric Acid (pH3)	Good	
	25% Hydrochloric Acid	Poor	Sealant Swelling
	10% Sulphuric Acid	Good	
	25% Sulphuric Acid	Good	
	10% Nitric Acid	Poor	Sealant Swelling
<b>Bases</b>	10% Soda (pH8)	Good	
	25% Soda	Poor	Adhesion Loss
	10% Potassium Chlorate	Good	
	25% Potassium Chlorate	Poor	Adhesion Loss
<b>Oil and Solvents</b>	Engine Oil	Very good	
	Methanol	Poor	Sealant Swelling
	Formol	Poor	Sealant Swelling
	Ethanol	Poor	Sealant Swelling
	Glycol	Very Good	
	Acetone	Poor	Sealant Swelling
	MEK	Poor	Sealant Swelling
	Ethyl Acetate	Poor	Sealant Swelling
	Toluene	Poor	Sealant Swelling
	Xylene	Poor	Sealant Swelling
	Chloric Solvents	Poor	Sealant Swelling
	Aliphatic Solvents	Good	
	Petrol	Poor	Sealant Swelling
	<b>Miscellaneous</b>	Water	Very good
Sea Water		Very Good	
Brine		Good	

This technical data sheet replaces all previous editions. The data on this sheet has been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.