

Stainless Steel 1.4541

Material Data Sheet

This data sheet applies for hot and cold rolled sheet and strip, semi-finished products, bars, rolled wire and profiles as well as seamless and welded tubes for pressure purposes.

Application

Instruments and construction parts in the food industry, luxury food, film and photo industry as well as for articles of daily use in the household, power station construction. Due to the Ti-alloy, the resistance to intergranular corrosion is also guaranteed in the welded condition.

Chemical Composition (heat analysis in %)

Product Form	C	Si	Mn	P	S	N	Cr	Ni	Ti
C, H, P	≤ 0.08	≤ 1.00	≤ 2.00	≤ 0.045	≤ 0.015 ¹⁾	-	17.00 - 19.00	9.00 - 12.00	5xC bis 0.70
L	≤ 0.08	≤ 1.00	≤ 2.00	≤ 0.045	≤ 0.030 ¹⁾	-	17.00 - 19.00	9.00 - 12.00 ²⁾	5xC bis 0.70
T _w	≤ 0.08	≤ 1.00	≤ 2.00	≤ 0.045 ³⁾	≤ 0.015 ³⁾	-	17.00 - 19.00	9.00 - 12.00	5xC bis 0.70
T _s	≤ 0.08	≤ 1.00	≤ 2.00	≤ 0.040	≤ 0.015 ¹⁾	-	17.00 - 19.00	9.00 - 12.00 ²⁾	5xC bis 0.70

C = cold-rolled strip H = hot-rolled strip P = hot rolled sheet L = semi-finished products, bars, rolled wire and profiles T_w = welded tubes
T_s = seamless tubes

¹⁾ A regulated sulphur content of 0.015 - 0.030 % has to be agreed for products, which have to be processed.

²⁾ If it should be necessary to minimise the content of the delta ferrite, the maximum content of nickel can be raised by 1%.

³⁾ For tubes, which are welded without filler metals, P + S 0.040 % max.

Mechanical Properties (at room temperature in annealed condition)

Product Form	Thickness mm max.	Yield Strength		Tensile Strength	Elongation min. in %		Impact Energy (ISO-V) ≥ 10mm thick	
		0.2% R _{p0.2} N/mm ²	1% R _{p1.0} N/mm ²	R ^m N/mm ²	A ¹⁾ %min (longitudinal)	A ¹⁾ %min (transverse)	J _{min} (longitudinal)	J _{min} (transverse)
C	8	220 ³⁾	220 ³⁾	520 - 720 ³⁾	-	40	-	-
H	13.5	200 ³⁾	240 ³⁾	520 - 720 ³⁾	-	40	100	60
P	75	200 ³⁾	240 ³⁾	500 - 700 ³⁾	-	40	100	60
L	160	190 ⁴⁾	225 ⁴⁾	500 - 700 ⁴⁾	40	-	100	-
L	250 ²⁾	190 ⁷⁾	225 ⁷⁾	500 - 700 ⁷⁾	-	30	-	60
T _w	60	180 ⁵⁾	215 ⁵⁾	460 - 680 ⁵⁾	35	30	100	60
T _s	60	180 ⁵⁾	215 ⁵⁾	460 - 680 ⁵⁾	35	30	100	60

¹⁾ Gauge length and thickness according to DIN EN

²⁾ > 160mm

³⁾ Transverse test piece, with product widths < 300mm long. test piece


⁴⁾ Longitudinal test piece

⁵⁾ Longitudinal test piece, external diameter > 508mm trans. test piece

⁶⁾ Hot Manufactured

⁷⁾ Transverse test piece

⁸⁾ at Rt and at -196°C



Reference data on some physical properties

Density at 20°C kg/dm ³	Modulus of Elasticity kN/mm ² at				Thermal Conductivity at 20°C W/m K	Specific Thermal Capacity at 20°C J/kg K	Specific Electrical Resistivity at 20°C Ω mm ² /m
	20°C	200°C	400°C	500°C			
7.9	200	186	172	165	15	500	0.73

Mean coefficient of thermal expansion 10 ⁻⁶ K ⁻¹ between 20°C and				
100°C	200°C	300°C	400°C	500°C
16.0	16.5	17.0	17.5	18.0

Guidelines on the temperature for hot forming and heat treatment¹⁾

Hot Forming		Heat Treatment		
Temperature °C	Type of Cooling	Temperature °C ²⁾³⁾⁴⁾	Type of Cooling	Microstructure
1150 to 850	Air	1000 to 1100	Water, air	Austenite with very few shares of ferrite

¹⁾ For simulative heat treatment test pieces the temperatures for solution annealing have to be agreed.

²⁾ Solution annealing is applicable if the conditions for the hot forming and the concluding cooling are in such a way that the requirements for the mechanical properties of the product can be maintained.

³⁾ If heat treatment is carried out in a continuous annealing furnace, usually the upper area of the mentioned temperature range is preferred or even exceeded.


⁴⁾ For heat treatment within subsequent processing, the lower area of the stated temperature range for solution annealing has to be aspired, as otherwise the mechanical properties could be affected. If the lower limit for the solution annealing temperature was not undercut during hot forming, while repeating annealing a temperature of 980°C as the lower limit is sufficient.

Processing / Welding

Standard welding processes for this steel grade are:

- TIG-Welding
- MAG-Welding Solid Wire
- Arc Welding (E)
- Submerged Arc Welding (SAW)
- Laser Beam Welding

Process	Filler Metal	
	Similar	Higher Alloyed
TIG	Thermanit H - 347 1.4551 Thermanit JE - 308L 1.4551	Thermanit A 1.4576
MAG Solid Wire	Thermanit H Si 1.4551 Thermanit JE - 308L Si 1.4551	Thermanit A Si 1.4576
Arc Welding (E)	Thermanit JE Sepcial 1.4551 Thermanit HW 1.4551 Thermanite HE Special 1.4551	Thermanit A Special 1.4576 Thermanit AW 1.4576



Stainless Steel 1.4541

Material Data Sheet

	Wire	Powder	Wire	Powder
SAW	Thermanit H-347 Thermanit JE-308L	Marathon 431 Marathon 213 Marathon 431 Marathon 213	Thermanit A Special	Marathon 431 Marathon 213
Laser Beam Welding	See Page 3			

When choosing the filler metal, the corrosion stress has to be regarded, as well. The use of a higher alloyed filler metal can be necessary due to the cast structure of the weld metal.

A preheating is not necessary for this steel. A heat treatment after welding is normally not usual.

Austenitic steels only have 30% of the thermal conductivity of non-alloyed steels. Their fusion point is lower than that of non-alloyed steel therefore austenitic steels have to be welded with lower heat input than non-alloyed steels. To avoid overheating or burn-through of thinner sheets, higher welding speed has to be applied. Copper back-up plates for faster heat rejection are functional, whereas to avoid cracks in the solder metal, it is not allowed to surface-fuse the copper back up plate.

This steel has an extensively higher coefficient of thermal expansion as non-alloyed steel. In connection with a worse thermal conductivity, a greater distortion has to be expected.

When welding 1.4541 all procedures, which work against this distortion (e.g. back step sequence welding, welding alternatively on opposite sides with double-V butt weld, assignment of two welders when the components are accordingly large) have to be respected notbaly. For product thicknesses over 12mm the double-V butt weld has to be preferred instead of the single-V butt weld. The included angle should be 60° - 70°, when using MIG-welding about 50° are enough. An accumulation of weld seams should be avoided. tack welds have to be affixed with relatively shorter distances from each other (significantly shorter than those of non-alloyed steels), in order to prevent strong deformation, shrinking or flaking tack weld. The tacks should be subsequently grinded or at least be free from crater cracks.

1.4541 in connection with austenitic weld metal and too high heat input the addiction to form heat cracks exists. The addiction to heat cracks can be confined, if the weld metal features a lower content of ferrite (delta ferrite). Contents of ferrite up to 10% have a favourable effect and do not affect the corrosion resistance generally. The thinnest layer as possible have to be welded (stringer bead technique) because a higher cooling speed decreases the addiction to hot cracks.

A preferably fast cooling has to be aspired while welding as well, to avoid the vulnerability to intergranular corrosion and embrittlement.

1.4541 is very suitable for laser beam welding (weldability A in accordance with DVS bulletin 3203, part 3). With a welding groove width smaller than 0.3mm respectively, 0.1mm product thickness, the use of filler metals is not necessary. With larger welding grooves a similar filler metal can be used. With avoiding oxidation within the seam surface during laser beam welding by applicable backhand welding, e.g. helium as inert gas, the welding seam is as corrosion resistant as the base metal. A hot crack hazard for the welding seam does not exist, when choosing an applicable process.

1.4541 is also suitable for laser beam fusion cutting with nitrogen or flame cutting with oxygen. The cut edges only have small heat affected zones and are generally free of micro cracks and thus are well formable. While choosing an applicable process the fusion cut edges can be converted directly. Especially, they can be welded without any further preparation.

While processing only stainless tools like steel brushes, pneumatic picks and so on are allowed, in order to not endanger the passivation.

It should be neglected to mark within the welding seam zone with oleigerous bolts or temperature indicating crayons.

The high corrossions resistance of this stainless steel is based on the formation of a homogeneous, compact passive layer on the surface. Annealing colours, scales, slag residues, tramp iron, spatters and such like have to be removed, in order to not destroy the passive layer.


For cleaning the surface the processes brushing, grinding, pickling or blasting (iron-free silica sand or glass spheres) can be applied. For brushing only stainless steel brushes can be used. Pickling of the previously brushed seam area is carried out by dipping and spraying, however, often pickling pastes or solutions are used. After pickling a careful flushing with water has to be done.

Remark

In quenched condition the material can be slightly magnetizable. With increasing cold forming the magnetizability increases.

Editor

thyssenkrupp Materials (UK) Ltd
Cox's Lane
Cradley Heath
West Midlands
B64 5QU



thyssenkrupp

thyssenkrupp Materials (UK) Ltd

Stainless Steel 1.4541

Material Data Sheet

Important Note

Information given in this data sheet about the condition or usability of materials respectively products are no warranty for their properties, but act as a description.

The information, we give on for advice, comply to the experiences of the manufacturer as well as our own. We cannot give warranty for the results of processing and application of the products.